



# DUPONT™ PYRALUX® LF SHEET ADHESIVE

## FLEXIBLE COMPOSITES

### DESCRIPTION

Sheet adhesive in the DuPont™ Pyralux® product line is a proprietary B-staged modified acrylic adhesive coated on release paper. Sheet adhesive is used primarily to bond flexible innerlayers or rigid cap layers in multilayer lamination. It is also widely used to bond flexible circuits to rigid boards during the fabrication of rigid-flex circuits, as well as to bond stiffeners and heat sinks.

### CONSTRUCTION

Sheet adhesive is available in a variety of thicknesses; see **Table 1**. The product code must be used when ordering sheet adhesive from DuPont.

**Table 1 - Sheet Adhesive Product Codes**

Product Code*	Adhesive Mil (μm)	IPC Certification*
LF0100	1 (25)	Yes
LF0200	2 (51)	Yes
LF0300	3 (76)	Yes
LF0400	4 (102)	Yes
LF1500	1/2 (13)	Yes
LF1700	.7 (18)	Yes
LF1800	.8 (20)	Yes
LF7049	1.5 (38)	Yes

\*Certified to IPC-4203/18: "Adhesive Coated Dielectric Films for Use as Cover Sheets for Flexible Printed Circuitry and Flexible Adhesive Bonding Films."

### PACKAGING

Sheet adhesive is supplied on 24-inch (610 mm) wide by 250 feet (76 m) long rolls, on nominal 3-inch (76 mm) cores. Narrower widths or cut sheets are also available by special order.

### TYPICAL DATA

Each manufactured lot of sheet adhesive is certified to IPC specifications and tested according to IPC Test Method TM-650. See **Table 2**.

**Table 2 - Sheet Adhesive Properties vs IPC Specifications**

Adhesive Property	IPC Spec	Typical Sheet Value
Peel Strength*, min., lb/in (kg/cm)		
As received	8 (1.4)	10 (1.8)
After solder	7 (1.3)	9 (1.6)
Solder Resistance 10 sec at 288°C (550°F)	Pass	Pass
Adhesive Flow, max. mil/mil adhesive (μm/μm)	5.0 (127)	2–4 (51–102)
Dielectric Constant, max. (at 1 MHz)	4.0	3.6–4.0
Dissipation Factor, max. (at 1 MHz)	0.05	0.02–0.03
Dielectric Strength volts/mil (kV/mm)	1,000 40	2,000–3,000 80–120
Insulation Resistance megohm	10 <sup>4</sup>	10 <sup>5</sup>
Volume Resistivity, min., megohm-cm (ambient)	10 <sup>7</sup>	10 <sup>9</sup>
Surface Resistivity, min., megohm-cm (ambient)	10 <sup>6</sup>	10 <sup>8</sup>

\*Laminating Conditions: 14kg/cm<sup>2</sup> (200 psi), 182°C (360°F), 1 hour to treated side of 1 oz RA copper foil. The values in Table 2 represent a typical 1 oz copper foil, 1 mil adhesive and 1 mil Kapton® construction.

A Certificate of Analysis is available with every batch. Complete material and manufacturing records for each lot, with samples of finished laminate, are retained for reference purpose. The roll labels contain the lot number, DuPont order number, customer order number, IPC specification, customer specification, and customer part number; save these labels for reference in case of inquiries.

### PROCESSING

Laminating conditions for Pyralux® flexible composites are typically in the following ranges:

Part Temperature:	182–199°C (360–390°F)
Pressure:	14–28 kg/cm <sup>2</sup> (200–400 psi)
Time:	1–2 hours, at temperature

For further processing information contact your DuPont representative to receive a Pyralux® Technical Manual.



## DUPONT™ PYRALUX® LF SHEET ADHESIVE

### STORAGE CONDITIONS AND WARRANTY

DuPont™ Pyralux® LF Sheet Adhesives should be stored in the original packaging at temperatures of 4–29°C (40–85°F) and below 70% humidity. The product should not be frozen and should be kept dry, clean and well protected. Subject to compliance with the foregoing handling and storage recommendations, the DuPont warranty, as provided in the DuPont Standard Conditions of Sale, shall remain in effect for a period of two years following the date of shipment.

### SAFE HANDLING

Pyralux® sheet adhesive contains a B-staged adhesive. Because B-staged adhesive contains trace quantities (parts per million) of unreacted monomers, precautions and recommendations should be taken to minimize contact.

DuPont is not aware of anyone developing contact dermatitis, or suffering any other medical discomforts, when using Pyralux® products. The uncured acrylic monomers in the bond ply adhesive may impart a mild odor. However, these products have been extensively tested under operating conditions (drilling and lamination conditions) and found to liberate measurable volatiles only well below<sup>1</sup> accepted safe limits (e.g., PEL).

To eliminate contact between the skin and the adhesive, wear lint-free gloves or fingerpads. Anyone handling Pyralux® should wash their hands with soap before eating, smoking, or using restroom facilities. Gloves and fingerpads should be changed daily, and wash other protective clothing frequently.

Adequate ventilation and exhaust is recommended in press rooms to prevent the buildup of potentially harmful vapors, to remove disagreeable odors, and to dissipate heat. Drill rooms should be furnished with standard equipment recommended by drill vendors and required by OSHA standards.

For further information on safe handling, refer to DuPont publication H-46862, “Pyralux® LF and FR Safe Handling;” and refer to “Industrial Ventilation,” 18th Edition or latest available from the American Conference of Governmental Industrial Hygienists, 6500 Glenway, Building D-5, Cincinnati, OH 45211.

<sup>1</sup>Values for all materials monitored were well below 10% of their accepted limits (PEL or TLV). In only one case, did the concentration reach approximately 40% of its limit. This was an oven used to dry the uncured acrylic material. This oven drying is not normally used in the process and during the exposure the oven was unventilated. Adequate ventilation is normally recommended for any heating process.

### FOR MORE INFORMATION ON DUPONT™ PYRALUX® FLEXIBLE CIRCUIT MATERIALS, PLEASE CONTACT YOUR LOCAL REPRESENTATIVE, OR VISIT OUR WEBSITE:

#### Americas

DuPont Electronic Technologies  
14 T. W. Alexander Drive  
Research Triangle Park, NC 27709  
Tel: 800-243-2143

#### Europe, Middle East & Africa

DuPont de Nemours  
(Luxembourg) s.à r.l.  
Rue Général Patton, Contern  
L-2984 Luxembourg  
Tel: +352 3666 5935

#### Japan

DuPont KK  
Sanno Park Tower  
11-1, Nagata-cho 2-chome  
Chiyoda-ku, Tokyo 100-6111  
Tel: 81-3-5521-8660

#### Taiwan

DuPont Taiwan Hsinchu Branch.  
#2, Li-Hsin 4th Rd., Hsinchu  
Science Park,  
Hsinchu 30078, Taiwan  
Tel: 886-3-5793654

#### India

E.I. DuPont India Limited  
1001-1012 “Meadows”, 10th  
Floor  
Sahar Plaza Complex  
Andheri-Kurla Road, Andheri  
(East)  
Mumbai 400 059, India  
Tel: 91-22-6751-5000  
DID: 91-22-6751-5038  
Fax : 91-22-67101937

#### China

DuPont China Holding Co., Ltd.  
Shanghai Branch  
Bldg. 11, 399 Keyuan Road  
Zhangjiang Hi-Tech Park  
Pudong New District  
Shanghai 201203, China  
Tel: 86-21-38622720

#### Korea

DuPont Korea Inc.  
4/5 Floor, Asia Tower  
#726, Yeoksam-dong, Kangnam-  
ku, Seoul  
135-082 Korea  
Tel: 82-2-2222-5224

#### Singapore

DuPont Singapore Pte, Ltd.  
1 HarbourFront Place #11-01  
HarbourFront Tower One  
Singapore 098633  
Tel: 65-6586-3091

[pyralux.dupont.com](http://pyralux.dupont.com)

Copyright © 2014 DuPont. All rights reserved. The DuPont Oval Logo, DuPont™, and all DuPont products denoted with ® or ™ are registered trademarks or trademarks of E. I. du Pont de Nemours and Company or its affiliates.

This information corresponds to our current knowledge on the subject. It is offered solely to provide possible suggestions for your own experiments. It is not intended, however, to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in end-use conditions, DuPont makes no warranties, and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see “DuPont Medical Caution Statement,” H-50102-4.

H-73246-6 09/14